



Dongre Laboratory Services Inc. (DLSI)

An AASHTO Accredited Laboratory
 2821Q Dorr Avenue
 (703) 395-8854, Fax: (540) 301-0839

REPORT ON SAMPLE(S) OF PERFORMANCE GRADED BINDER

Hanburn Wheel Tracker Report

Project Name:	Rubber Asphalt Solutions	Date:	10/18/08
Project Number:	LA DOT Crumb Rubber Dry Process	Date Sampled:	N/A
Job Number:		Lab Number:	DLSI-RAS_LADOT_QC_Samples_#1
Project Engineer:	Raj Dongre	Mix Type:	Crumb Rubber - Dry Process
Submitted By:	Frank Davis	Asphalt Grade:	
Average Test Temperature, °C	50 - Wet	Pit Source:	N/A

No. of Passes at Failure:	19975.00	Max. Rut Depth:	-3.67 mm (Avg. LVDT Pos. 6)
---------------------------	----------	-----------------	--------------------------------

		PASSED	Pass/Fail:	
Rutting Slope	-8.0106E-05	mm/cycle		
Stripping Slope	N/A	mm/cycle		
Inflection Point	N/A	cycles		

