



**DONGRE
LABORATORY
SERVICES**

Dongre Laboratory Services Inc.
2821Q Dorr Avenue, Fairfax, VA - 22031
Tel: (703) 395-8854, Fax: (540) 301-0839

An AASHTO Accredited Laboratory

Consulting and Testing Services in Asphalt Technology

REPORT ON SAMPLE(S) OF PERFORMANCE GRADED BINDER		DLSI
DLSI Internal ID		
Material Supplier	Jim Stepp	
Supplier ID		A
PG Grade		PG 76-22
Continuous PG Grade		PG 81.76-22.77
Un-aged Binder Tests:		
Viscosity-Rotational, cP 135 C	T316	1.660
Flash Point, C	T48	310
Cigar Cubes Separation at 163C 48 hours		
Softening Point, Top, F	T53	125.2
Softening Point, Bottom, F	T53	153.0
Difference	<18F between top and bot	-27.8
Dynamic Shear Rheometer	T315	
	Temp Pass	76
Phase Angle, degrees		82.1
G* @10 rad/sec, kPa		1.92
G*/sin delta @10 rad/sec, kPa		1.94
	Temp Fail	82
Phase Angle, degrees		84.9
G* @10 rad/sec, kPa		0.98
G*/sin delta @10 rad/sec, kPa		0.98
Pass/Fail Temp		81.8
RTFO Residue Tests:		
Mass Loss, %	T 240	-0.195
Dynamic Shear Rheometer	T 315	
	Temp Pass	82
Phase Angle, degrees		73.1
G* @10 rad/sec, kPa		2.63
G*/sin delta @10 rad/sec, kPa		2.75
	Temp Fail	88
Phase Angle, degrees		76.5
G* @10 rad/sec, kPa		1.44
G*/sin delta @10 rad/sec, kPa		1.48
Pass/Fail Temp		84.2
Multiple Stress Creep Recovery AASHTO TP 70		67
Jnr, 3.2 kPa average	max Jnr at 3.2 kPa = 1.0	0.40
%R3.2 > (29.37(Jnr,3.2)^-0.2632)	37	29
PAV Residue Tests:		
Dynamic Shear Rheometer	T 315	
	Temp	31
Phase Angle, degrees		42.6
G* @10 rad/sec, kPa		3270
G*/sin delta @ 10 rad/sec, kPa		2210
Direct Tension Test	T 314	
	Temp Pass	-12
Strain, 1.0 mm/min		1.45
Stress, Mpa		2.402
Bending Beam Rheometer	T 313	
	Temp Pass	-12
s, 60s, Mpa		175
M-value, 60s		0.305
	Temp Fail	-18
s, 60s, Mpa		293
M-value, 60s		0.266
Notes:		